## Assay Results – New OKO Discovery

| DRILL HOLE | FROM (metres) | TO (metres) | INT. (metres) | GRADE g/t Au | Grade x DH Width |
|---|---|---|---|---|---|
| **AMD26** | | *No significant intercept.* | | | |
| **AMD27** | 77.0 | 80.0 | 3.0 | 1.0 | **2.9** |
| **AMD27** | 90.5 | 93.5 | 3.0 | 3.4 | **10.1** |
| **AMD28** | | *No significant intercept.* | | | |
| **AMD29** | 23.5 | 34.0 | 10.5 | 0.6 | **6.7** |
| **AMD30** | 80.5 | 82.0 | 1.5 | 1.8 | **2.7** |
| **AMD30** | 90.0 | 150.0 | 60.0 | 5.9 | **351.2** |
| ***Incl.*** | *127.5* | *150.0* | *22.5* | *9.3* | ***209.0*** |
| **AMD31** | 20.0 | 27.5 | 7.5 | 1.1 | **8.4** |
| **AMD32** | | *No significant intercept.* | | | |
| **AMD33** | | *No significant intercept.* | | | |
| **AMD34** | *103.5* | 111.0 | *7.5* | *3.2* | ***24.0*** |
| **AMD35** | *73.5* | 105.5 | *32.0* | *0.4* | ***11.9*** |
| **AMD36** | 57.5 | 63.5 | 6.0 | 0.4 | **2.4** |
| **AMD37** | *83.5* | 134.5 | *51.0* | *3.0* | ***150.5*** |
| ***Incl.*** | *89.5* | 100.0 | *10.5* | *6.3* | ***66.3*** |
| **AMD38** | 118.0 | 132.0 | *14.0* | *1.1* | ***16.1*** |
| **AMD38** | *153.0* | 185.0 | *32.0* | *0.4* | ***13.2*** |

| | | | | | |
|---|---|---|---|---|---|
| **AMD39** | *No significant intercept.* | | | | |
| **AMD40** | 6.5 | 11.0 | 4.5 | 1.4 | **6.3** |
| **AMD40** | 44.0 | 45.5 | 1.5 | 3.8 | **5.7** |
| **AMD41** | *33.0* | 75.0 | *42.0* | *2.2* | ***93.8*** |
| ***Incl.*** | *33.0* | *37.5* | *4.5* | *9.3* | ***41.9*** |
| **AMD42** | 183.0 | 236.0 | 53.0 | 0.5 | **26.2** |
| **AMD43** | 64.0 | 65.0 | 1.0 | 0.4 | **0.4** |
| **AMD44** | 72.5 | 75.5 | 3.0 | 1.0 | **2.9** |
| **AMD45** | 168.0 | 206.5 | 38.5 | 0.6 | **21.3** |
| **AMD46** | 128.0 | 129.5 | 1.5 | 0.5 | **0.8** |
| **AMD47** | *No significant intercept.* | | | | |
| **AMD48** | 18.5 | 21.0 | 2.5 | 0.6 | **1.6** |
| **AMD48** | 46.0 | 65.5 | 19.5 | 0.6 | **11.7** |
| **AMD49** | 62.5 | 64.0 | 1.5 | 1.1 | **1.7** |
| **AMD49** | 207.0 | 227.0 | 20.0 | 1.1 | **22.2** |
| **AMD50** | 52.5 | 152.4 | 99.9 | 2.2 | **224.4** |
| ***Incl.*** | *74.0* | *99.5* | *25.5* | *5.5* | ***141.3*** |

*Notes to Table 1: Intercepts reported are down-hole widths. True widths are estimated between 49% and 93% of reported down-hole widths. Average grades are calculated with un-capped gold assays, as insufficient drilling has been completed to determine capping levels for higher grade intercepts.*